

## Tackwhite AP 32

### Description

TACKWHITE AP 32 is a water-based pressure sensitive adhesive, based on acrylic latices.

### Application

TACKWHITE AP 32 has been designed for the production of protective PE films.

### Technical Specifications

Method of analysis	MU	Standard
1. <b>Total Solids</b>	%	50±2
3. <b>Brookfield Viscosity</b> 25°C	cps	50 - 200
8. <b>pH</b>	pH	8.5 - 9.5
- <b>Solvents</b>		water

### Film properties

Method of analysis	MU	Standard
11. <b>Peel Adhesion on Steel</b>	g/in	300 - 600
17. <b>Rolling Ball Tack</b>	cm	5 - 10
22. <b>Holding Power of</b> <b>Pressure Sensitive</b> <b>Tapes</b>	h	> 10

Average values; 22±2 g/m<sup>2</sup> of dry adhesive on PES film 23 µm

### Handling

It is necessary to cure the product with Xama 7 (0.5-1.5%) or CURING AGENT W3 DIL.(1-2%). After addition of curing agent, pot-life decreases, it depends on the temperature and pH.

### Packing

TACKWHITE AP 32 can be supplied in 200 l iron drums or in 1000 l plastic tanks.

### Storing

TACKWHITE AP 32 must be stored at temperature between +5°C and +40°C.

If stored in original packaging shelf life is 3 months. Keep containers well closed, in order to avoid surface skin formation.