



Tacksol 10/76 BW

(Provisional)

Description

TACKSOL 10/76 BW is a solvent borne pressure sensitive adhesive, based on natural rubber and special resins. After curing, the product has a very high cohesion, medium tack and low adhesion.

Application

TACKSOL 10/76 BW is recommended for the production of BW PE protective films and tapes for very smooth surfaces.

Packaging

The product is supplied in iron drums (145 kg); ADR compliant IBC containers (750 kg).

Storing

Stir before use. Keep containers well closed to prevent solvent evaporation. Store at temperatures between +5 and + 40°C, protected from heat sources and direct sunlight.

Use within 12 months from production date (unopened and in the original packaging).

Technical Specifications

Method of analysis	MU	Standard
--------------------	----	----------

1. Total Solids	%	27±1
3. Brookfield Viscosity	mPa.s	< 1500 ⁽¹⁾
25°C		
Solvents		hexane

⁽¹⁾ N. 2 RV; 20 RPM

Handling

TACKSOL 10/76 BW can be diluted with aliphatic and aromatic solvents in order to achieve the desired viscosity. For protective tapes the product must be cured with CURING AGENT D or CURING AGENT P65 (0.5 - 1%). Reaction starts immediately, so it is recommended to use the product immediately after the activation. The crosslinking mechanism depends on different aspects as adhesive concentration, amount of crosslinker, temperature. We suggest to check in advance curing conditions, in order to avoid to spoil material.