



Release WR 2503 Dil. 2

(Provisional)

Use within 9 months from production date
(unopened and in the original packaging).

Description

RELEASE WR 2503 DIL. 2 is a special water based release coating developed for Pressure Sensitive Adhesive tapes to provide controlled release effect.

Application

RELEASE WR 2503 DIL. 2 adheres well to treated polyolefins. It provides excellent release on adhesive coated polyolefines/PET.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids Solvents	%	2±0.10 water

Handling

RELEASE WR 2503 DIL. 2 is ready for coating by Meyer Bar or Gravure rolls. Apply 4 - 5 g (wet)/sqm on corona treated polyolefin (approx. 35 dyne/cm). Release action is developed by evaporation of the water at 80 - 100°C, depending upon web speed and oven efficiency. No curing mechanism is involved.
It is suggested to stir before use.

Packaging

The product is supplied in iron drums (200 kg); IBC containers (1000 kg).

Storing

Product must be stored at temperatures between +5 and +35°C.