



## Tackwhite AL 4

### Description

Carboxylated Styrene-Butadiene water dispersion, soft hand and no residual tack. Good frothing behaviour.

### Application

Textile/non woven/paper/leather binder and wet adhesive.

### Technical Specifications

| Method of analysis              | MU    | Standard                |
|---------------------------------|-------|-------------------------|
| 1. Total Solids                 | %     | 46±1                    |
| 8. pH                           |       | 8                       |
| 3. Brookfield Viscosity<br>25°C | mPa.s | 50 - 250 <sup>(1)</sup> |
| Solvents                        |       | water                   |

<sup>(1)</sup> No 2 RV; 50 RPM

### Handling

Can be added with acrylic thickeners to increase viscosity, wetting agents, defoamers, etc. It can be applied by knife, reverse roll, mayer bar, etc.

### Packaging

The product is supplied in iron drums (200 kg); IBC containers (1000 kg).

### Storing

Keep at temperatures between +5 and 40°C, closed containers.

Use within 6 months from production date (unopened and in the original packaging).