



Packaging

Storing

conditions.

IBC containers (1000 kg).



UNI EN ISO 9001:2015 UNI EN ISO 14001:2015 UNI ISO 45001:2018

The product is supplied in plastic drums (150 kg);

TACKWHITE AR 35 must be stored at temperatures

between +5°C and +40°C, avoiding freezing

Use within 6 months from production date (unopened and in the original packaging).

Tackwhite AR 35

(Provisional)

Description

TACKWHITE AR 35 is a removable pressure sensitive adhesive, based on acrylic polymers in water dispersion. It displays very good resistance to water and to plasticizers.

Application

TACKWHITE AR 35 is a removable p.s.a. for plastic film labels in PVC, PE and BOPP.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids 3. Brookfield Viscosity 25°C	% mPa.s	52±2 < 1000 ⁽¹⁾
8. pH	рН	6.5 - 9
⁽¹⁾ No 1 RV; 20 RPM		

Film properties

Method of analysis	MU	Standard
11. Peel Adhesion on Steel	g/in	500
17. Rolling Ball Tack 22. Static Shear	cm h	10 > 100

Average values; 22 ± 2 g/m² of dry adhesive on PET film 36 μ m

Handling

TACKWHITE AR 35 is designed for the application on glass, especially for bus marking. The surface is usually wetted with water and the coated material is applied by manual pressure to drain any excess of water.

Mod. DT0104E - Tackwhite AR 35 Creation date: 26 Jun 2008 Revision: 5 Revision date: 12 Mar 2018

Above information is reliable, but does not constitute warranty.