



Packaging

Storing

and direct sunlight.



necessary to cure the product with CURING AGENT RF/AEDE (0.5 - 2%); in this case, the pot-life of the

immediately after the addition of the curing agent.

The product is supplied in iron drums (145 kg).

Store at temperatures between +5 and + 40°C in

well closed containers. Keep far from heat sources

Use within 12 months from production date (unopened and in the original packaging).

adhesive is reduced as crosslinking starts

Tacksol 10/86 EPM

Description

TACKSOL 10/86 EPM is a solvent borne pressure sensitive adhesive, based on natural rubber and special resins. It displays a good wettability on various substrates.

Application

TACKSOL 10/86 EPM can be applied on any substrate (paper, PET, PP, PE, PVC). It is a soft adhesive and is reccomended for the production of protective p.s. films and tapes.

Technical Specifications

Method of analysis	MU	Standard	
1. Total Solids 3. Brookfield Viscosity 25°C Solvents	% mPa.s	17±1 300 - 700 ⁽¹⁾ heptane	
⁽¹⁾ No 1 RV; 10 RPM			

Film properties

Method of analysis	MU	Standard
11. Peel Adhesion on Steel	g/in	500
17. Rolling Ball Tack 97. Loop Tack Test	cm g	7 1,200

Average values; 22±2 g/m² of dry adhesive on PET film 36 μm

Handling

TACKSOL 10/86 EPM can be diluted with aliphatic and aromatic solvents in order to achieve the desired viscosity. For protective tapes it is

Mod. DT0104E - Tacksol 10/86 EPM Creation date: 8 Oct 2008 Revision: 4 Revision date: 23 May 2017

Above information is reliable, but does not constitute warranty.