





## Tackwhite SB 5

### **Description**

TACKWHITE SB 5 is a water-borne pressure sensitive adhesive, based on anionic dispersion of carboxylated-modified SBR latex and water tackifiers (rosin esters), properly stabilised.

TACKWHITE SB 5 has very good stability when stored at temperature between + 10°C and + 40°. It allows to obtain very good p.s.a. articles, being stabilised with very effective antioxidants. However, containing rubber based lattices, it produces opaque and slightly yellowish films.

### **Application**

Permanent paper labels, self adhesive fabrics, synthetic and natural leathers, paper boards, polyurethane and polyethylene foams, double sided adhesives etc.

## **Technical Specifications**

Method of analysis	MU	Standard
1. Total Solids 8. pH Solvents	% pH	56±2 8 - 9 water / toluene
3. Brookfield Viscosity 25°C	mPa.s	
TACKWHITE SB5 (V1)		12,000 - 22,000 <sup>(1)</sup>
TACKWHITE SB5 (V2)		17,000 - 27,000 (2)
TACKWHITE SB5 (V3)		27,000 - 37,000 <sup>(2)</sup>

<sup>&</sup>lt;sup>(1)</sup> N. 5 RV; 20 RPM

#### Film properties

Method of analysis	MU	Standard
11. Peel Adhesion on Steel	g/in	1,900
17. Rolling Ball Tack	cm	12
22. Static Shear	h	> 5
97. Loop Tack Test	g	1,100

Average values; 22±2 g/m² of dry adhesive on PET film 36 μm

## Handling

Cohesion can be increased by a moderate addition of CURING AGENT W3 or Curinga Agent X7.

# **Packaging**

The product is supplied in iron drums (200 kg); IBC containers (1000 kg).

# **Storing**

TACKWHITE SB 5 must be stored at temperatures between +5°C and +40°C.

Use within 6 months from production date (unopened and in the original packaging).

uild date 17 Sen 2020

Mod. DT0104E - Tackwhite SB 5 Creation date: 12 Jan 1996 Revision: 6 Revision date: 29 Jun 2016 1/1

<sup>&</sup>lt;sup>(2)</sup> No 6 RV; 20 RPM