

Tacksol 10/84

OBSOLETE

Description

TACKSOL 10/84 is a solvent borne pressure sensitive adhesive, based on natural rubber and special resins. After curing, it develops very good resistance to ageing, light and heat. It has been formulated to obtain a low noise effect during the unwinding process.

Application

TACKSOL 10/84 can be applied on any substrate (PET either release-coated or not, PP, PE, PVC). This product is recommended for the production of protective p.s. films and tapes.

Handling

When heat or mechanical resistance needs to be increased, 0.5 - 1% of CURING AGENT D should be added. Crosslinking starts immediately after the addition of the curing agent.

Storing

Store at temperatures between +5 and +40°C. Keep containers well closed, protected from heat sources and direct sunlight.

Technical Specifications

Method of analysis	MU	Standard
Solvents		hexane
1. Total Solids	%	
TACKSOL 10/84		30±1
3. Brookfield Viscosity 25°C	mPa.s	
TACKSOL 10/84		600 - 1,800 ⁽¹⁾
⁽¹⁾ N. 2 RV; 20 RPM		

Film properties

11. Peel Adhesion on Steel	g/in	
TACKSOL 10/84		200
17. Rolling Ball Tack	cm	
TACKSOL 10/84		3
22. Static Shear	h	
TACKSOL 10/84		> 100

Average values; 22±2 g/m² of dry adhesive on PET film 36 µm