



## S.L. 60

(Provisional)

Use within 6 months from production date  
(unopened and in the original packaging).

### Description

S.L..60 is an acrylic latex in anionic water emulsion.  
The product is APEO free. Tg = -11°C

### Application

S.L..60 can be used as binder for textile, paper, etc  
without residual tack.

It has a very soft hand after drying. Applied on  
fabrics, it is resistant to washing and rubbing.

### Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	45±1
3. Brookfield Viscosity 25°C	mPa.s	50 - 200 <sup>(1)</sup>
8. pH Solvents	pH	6 - 7 water

<sup>(1)</sup> No 1 RV; 20 RPM

### Handling

The product can be applied with: Mayer  
bar, foulard, rotogravure, air knife and, once  
thickened, with blade coating.

### Packaging

The product is supplied in plastic drums (120 kg);  
IBC containers (1000 kg).

### Storing

S.L..60 must be stored at temperature between +5  
and +40°C .