





# **Tackwhite AK 11**

(Provisional)

### **Description**

TACKWHITE AK 11 is a water borne pressure sensitive adhesive based on acrylic polymers. It has a very good anchorage on corona treated polyolefin films.

The coated product has a very high resistance to plasticizers and its adhesive properties are stable after ageing.

# **Application**

TACKWHITE AK 11 is suggested for the production of film labels.

## **Technical Specifications**

Method of analysis	MU	Standard
1. Total Solids 8. pH Solvents	% pH	50±1 7 - 8 water
3. Brookfield Viscosity 25°C	mPa.s	
TACKWHITE AK 11		150 - 400 <sup>(1)</sup>
TACKWHITE AK 11 (V500)		400 - 550 <sup>(1)</sup>
<sup>(1)</sup> No 1 RV: 20 RPM		

# **Film properties**

Method of analysis	MU	Standard
11. Peel Adhesion on Steel	g/in	1,000
17. Rolling Ball Tack	cm	6
22. Static Shear	h	> 50
97. Loop Tack Test	g	900

Average values;  $22\pm2$  g/m $^2$  of dry adhesive on PET film 36  $\mu m$ 

## **Handling**

The product can be applied by Mayer bar or reverse roll.

If necessary, it can be thickened with a suitable acrylic based thickener.

### **Packaging**

The product is supplied in plastic drums (225 kg); IBC containers (1050 kg).

## **Storing**

TACKWHITE AK 11 must be stored at temperature between +5°C and +30°C. Protect from freeze.

Use within 6 months from production date (unopened and in the original packaging).