



## S.L. 24

(Provisional)

### Description

S.L. 24 is a water dispersion of a SBR latex.  
Tg = - 35°C

### Application

S.L. 24 is used as binder for fabrics, paper, ...The product has a minimum residual tack.

### Storing

Keep at temperatures between +5 and +40°C.  
Protect from freezing.  
Use within 6 months from production date (unopened and in the original packaging).

### Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	56±1
3. Brookfield Viscosity 25°C	mPa.s	< 800 <sup>(1)</sup>
8. pH Solvents	pH	7 - 9 water

<sup>(1)</sup> No 2 RV; 50 RPM

### Handling

S.L. 24 is extremely compatible with natural latex and it can be considered a synthetic alternative to this product. S.L. 24 can be formulated with tackifiers, thickeners, surfactants, pigments in dispersion, etc.

S.L. 24 can be applied with traditional methods: mayer bar, foulard, rotogravure, air blade, etc.

### Packaging

The product is supplied in iron drums (200 kg); IBC containers (1000 kg).