





# **Tackwhite A 238**

(Provisional)

#### **Description**

TACKWHITE A 238 is an APEO free water based acrylic pressure sensitive adhesive. The dried film has a very aggressive initial tack and a good cohesion.

#### **Application**

Thanks to its high cohesion, TACKWHITE A 238 is suitable for the production of pressure sensitive packaging tapes on BOPP films. Recommended coating weight is 15-18 g/sqm dry.

TACKWHITE A 238 can be formulated with resins/tackifiers in order to obtain a product for other applications, such as labels, foams, synthetic leather, fabrics,...

### **Technical Specifications**

Method of analysis	MU	Standard
1. Total Solids	%	60±1
<ol> <li>Brookfield Viscosity</li> <li>25°C</li> </ol>	mPa.s	200 - 700 (1)
8. pH		5 - 7
Solvents		water
<sup>(1)</sup> N. 2 RV; 20 RPM		

## Film properties

Method of analysis	MU	Standard
11. Peel Adhesion on Steel	g/in	750
17. Rolling Ball Tack	cm	5
22. Static Shear	h	> 200
97. Loop Tack Test	g	1,000

Average values;  $22\pm2$  g/m<sup>2</sup> of dry adhesive on PET film 36  $\mu$ m

#### **Packaging**

The product is supplied in iron drums (200 kg); IBC containers (1000 kg).

# **Storing**

Keep containers well sealed to prevent water evaporation and skin formation. The emulsion must be stored between +5 and +40°C. Freezing must be avoided.

Use within 6 months from production date (unopened and in the original packaging).