





### Solacril 303

(Provisional)

## **Description**

SOLACRIL 303 is a solvent borne acrylic PSA, with a very good resistance to ageing, light and heat.

# **Application**

SOLACRIL 303 can be applied on various substrates: paper, polyester, PP, PE, PVC, etc. After curing it is recommended for protective films.

#### **Technical Specifications**

Method of analysis	MU	Standard
1. Total Solids 3. Brookfield Viscosity 25°C Solvents	% mPa.s	50±1 3,000 - 7,000 <sup>(I)</sup> ethylacetate
<sup>(1)</sup> N. 4 RV; 20 RPM		

# Film properties

Method of analysis	MU	Standard	
11. Peel Adhesion on Steel	g/in	450 <sup>(1)</sup>	
97. Loop Tack Test	g	650 <sup>(1)</sup>	
(1) Crosslinked with 0.3% of CURING AGENT CH			

Average values; pilot plant coating at 1 m/min; 18 $\pm$ 3 g/m² on PET film 23  $\mu$ m, TCA-treated

# Handling

SOLACRIL 303 must be activated before use, to increase adhesion to plastic films and to improve

#### cohesion.

Suggested activators are: CURING AGENT CH, CURING AGENT D or RF/AEDE. Reaction starts immediately, so it is recommended to use the product after activation. The quantity of crosslinker depends on the coating weight and on the desired final properties, usually it is between 0.2 and 1.5%. We suggest to check in advance the curing conditions.

## **Packaging**

The product is supplied in iron drums (200 kg); ADR compliant IBC containers (900 kg).

#### **Storing**

Store in a cool place, protected from direct sunlight and heat sources, at temperatures between +5 and +40°C. Keep material in tightly closed containers to prevent loss of solvent. Use within 6 months from production date (unopened and in the original packaging).

Build date 17 Sep 2020