





# **Tackwhite A 916**

(Provisional)

#### **Description**

TACKWHITE A 916 is a waterborne pressure sensitive adhesive, based on acrylic polymers, with medium-high tack and peel adhesion.

It yields a transparent film with a good anchorage on many different surfaces.

## **Application**

Insulating foams; paper and film labels; self adhesive fabrics; synthetic leathers; paper and paperboards.

We recommend to check the compatibility with the support before using the product.

### **Technical Specifications**

Method of analysis	MU	Standard
1. Total Solids Solvents	%	67±2 water
<ol> <li>Brookfield Viscosity</li> <li>25°C</li> </ol>	mPa.s	
TACKWHITE A 916		500 - 1,000 <sup>(1)</sup>
TACKWHITE A 916 (V1)		11,000 - 22,000 <sup>(2)</sup>
TACKWHITE A 916 (V2)		17,000 - 27,000
8. pH	рН	
TACKWHITE A 916		7 - 8
TACKWHITE A 916 (V1)		7 - 9
TACKWHITE A 916 (V2)		7 - 9

<sup>(</sup>I) No 1 RV; 20 RPM

## Film properties

Method of analysis	MU	Standard
11. Peel Adhesion on	g/in	900

22. Static Shear h > 50 97. Loop Tack Test g 1,600

Average values;  $22\pm2$  g/m² of dry adhesive on PET film 36  $\mu$ m

#### **Handling**

TACKWHITE A 916 can be directly or transfer coated on polyethylene, polypropylene, PVC, fabrics. It can be applied by reverse roll, knife coating, and similar.

### **Packaging**

The product is supplied in iron drums (200 kg); IBC containers (1000 kg).

### **Storing**

Product must be stored at temperatures between +5°C and +40°C, avoiding freezing conditions.

1/1

Use within 6 months from production date (unopened and in the original packaging).

<sup>(2)</sup> N. 5 RV; 20 RPM