



When heat or mechanical resistance must be increased, CURING AGENT D should be added. In

of the curing agent. The amount of isocyanate

The product is supplied in iron drums (145 kg).

Product must be stored in a ventilated and dry

Use within 12 months from production date (unopened and in the original packaging).

place. Avoid flames presence.

depends on the final properties requested.

Packaging

Storing

this case the pot-life of the adhesive is reduced as crosslinking starts immediately after the addition



UNI EN ISO 9001:2015 UNI EN ISO 14001:2015 UNI ISO 45001:2018

Tacksol NIS 6

(Provisional)

Description

TACKSOL NIS 6 is a solvent pressure sensitive adhesive, based on different rubbers and special resins, with very high peel adhesion.

Application

TACKSOL NIS 6 can be applied on any substrate (textile, TNT, paper, polyester, PP, PE, PVC). It is suggested when high adhesivity, high tack and good cohesion are required.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids 3. Brookfield Viscosity 25°C Solvents	% mPa.s	48±1 30,000 - 45,000 ⁽¹⁾ toluene
⁽¹⁾ No 6 RV; 10 RPM		

Film properties

Method of analysis	MU	Standard
11. Peel Adhesion on Steel	g/in	2,000
96. S.A.F.T. ⁽¹⁾	°C	120
97. Loop Tack Test	g	3,000

¹⁾ based on ASTM D4498-00

Average values; 22±2 g/m² of dry adhesive on PET film 36 μm

Handling

TACKSOL NIS 6 can be coated with rotating knife or knife-on-roll.

Build date 18 Sep 2024

Mod. DT0104E - Tacksol NIS 6 Creation date: 10 Dec 2018 Revision: 2 Revision date: 4 Feb 2020

Above information is reliable, but does not constitute warranty.

1/1