



50°C till complete dissolution of the powder. Handle with care, since the solvent is flammable.

Before coating, it is recommended to stir and

The product is supplied in fibre drums (20 kg).

RELEASE S 100 in 100% solid form can be stored

safely at any temperature below its melting point. In solution, it must be stored at temperatures not

below 25°C to prevent gelification. In case of partial or total solidification, store the product in a heated

35°C to 50°C before use. The product will return as

place and stir it well at a temperature between

Do not coat if liquid is not completely clear or

Use within 24 months from production date

(unopened and in the original packaging).

heat the solution at 30°C at least.

Packaging

Storing

fluid as before.

if gelification occured.



UNI EN ISO 9001:2015 UNI EN ISO 14001:2015 UNI ISO 45001:2018

Release S 100

(Provisional)

Description

RELEASE S 100 is a PVSC (*Polyvinyl stearyl carbamate*), a synthetic polymer with high molecular weight in 100% solid powder form. When in solution, it is a very efficient release agent for polyolefins and substrates with low melting points (PE, PP, PVC, PET), coated with natural rubber, synthetic rubber and/or acrylic adhesives. New version with high purity, enhanced solubility and easier release effect.

The product is silicone free.

Application

RELEASE S 100 can be used on corona treated as well as on untreated films. Concentration ranges from 0.3% solid to 2% solids, depending upon film, type, coating equipment and desired release force. **RELEASE S 100** is soluble in aromatic and aliphatic solvents (hexane, heptane, octane, pure and in blends with IPA 3/1) at temperatures above 35°C.

In order to achieve a continuous and homogenous coating, the RELEASE S 100 must be completely dissolved and the solution must be clear and homogeneous.

Technical Specifications

Method of analysis	MU	Standard	
1. Total Solids	%	99±1	
5. Melting Range	°C	85 - 95	

Handling

Slowly add **RELEASE S 100** to the solvent and stir continuously at a temperature between 35 and

Build date 18 Sep 2024

Mod. DT0104E - Release S 100 Creation date: 11 Feb 2020 Revision: 1 Revision date: 11 Feb 2020

Above information is reliable, but does not constitute warranty.

1/1