



sources and direct sunlight.

Storing



UNI EN ISO 9001:2015 UNI EN ISO 14001:2015 UNI ISO 45001:2018

Stir before use . Keep containers well closed to

between +5 and + 40°C, protected from heat

Use within 12 months from production date (unopened and in the original packaging).

prevent solvent evaporation. Store at temperatures

Tacksol 20/83 LHX

(Provisional)

Description

TACKSOL 20/83 LHX is a pressure sensitive adhesive, based on natural rubber and special resins dissolved in hexane. After curing, the product has a very high cohesion, medium tack and medium adhesion.

Application

TACKSOL 20/83 LHX is recommended for the production of BW PE protective films and tapes for smooth surfaces and PVC.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids Solvents	%	17±1 hexane

Handling

TACKSOL 20/83 LHX can be diluted with aliphatic and aromatic solvents in order to achieve the desired viscosity. For protective tapes the product must be cured with CURING AGENT P65 (0.5 - 2%). Reaction starts immediately, so it is recommended to use the product in a short time after the activation. The crosslinking mechanism depends upon different aspects as adhesive concentration, amount of crosslinker, temperature. We suggest to check in advance curing conditions, in order to avoid to spoil material.

Packaging

The product is supplied in iron drums (145 kg).

Mod. DT0104E - Tacksol 20/83 LHX Creation date: 15 Oct 2020 Revision: 1 Revision date: 15 Oct 2020

Above information is reliable, but does not constitute warranty.