



Tacksol IS 48/40

(Provisional)

Description

TACKSOL IS 48/40 is a solvent-borne PSA, based on synthetic rubber, and both natural and synthetic resins. It has excellent ageing stability.

Application

The product is highly recommended when good tack, very high cohesion and good thermic resistance are demanded.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	40±1
3. Brookfield Viscosity 25°C	mPa.s	500 - 1,000 ⁽¹⁾
Solvents		toluene

⁽¹⁾ N. 2 RV; 20 RPM

Packaging

The product is supplied in iron drums (145 kg).

Storing

The product must be stored at temperatures between +5 and +30 °C.

Use within 12 months from production date (unopened and in the original packaging).

Notes

The product, once coated, is subject to oxidation from air and light and must be protected in order not to compromise its performance.

Film properties

Method of analysis	MU	Standard
11. Peel Adhesion on Steel	g/in	2,000
22. Static Shear	h	> 100
97. Loop Tack Test	g	> 1,300

Average values; 22±2 g/m² of dry adhesive on PET film 36 µm

Handling

TACKSOL IS 48/40 can be coated with the most common coating system (blade, reverse roll, etc.).