



The product shall be stored in cool and dry

conditions, protected from humidity, heat, sunlight

Once opened, each individual package should be used completely to avoid hydrolysis. Storage at

elevated temperatures, exposure to direct heat and/or moisture could significantly decrease

Use within 24 months from production date

(unopened and in the original packaging).

Storing

and water.

product shelf life.



UNI EN ISO 9001:2015 UNI EN ISO 14001:2015 UNI ISO 45001:2018

# **Antiox UV-STE**

#### Description

ANTIOX UV-STE is a sinergic blend of various antioxidants (primary phenolic stabilizers -phosphite -thioester) and an UV stabilizer (UV Absorber). The product is dust free and free flowing.

## Application

This product is suitable for a complete stabilization towards UV light and heat; it has a wide protection range. It can be used both for hot-melt and solvent borne elastomeric systems.

APPLICATION: PSAs and adhesives for coating, injection moulding or extrusion.

## **Technical Specifications**

Method of analysis	MU	Standard
1. Total Solids	%	99±1
5. Melting Range	°C	50 - 190

## Handling

ANTIOX UV-STE can be introduced directly in the mixture with other components of the formulation or it can be dissolved if there is a solvent. It is suggested to use a liquid component (a rosin ester or a napthenic oil) in extrusion hot-melt continuous systems, this permits an homogeneous mixing of the antioxidant with the total mass (volumetric dosage).

## Packaging

The product is supplied in fiber drums (50 kg).

Mod. DT0104E - Antiox UV-STE Creation date: 31 May 2022 Revision: 3 Revision date: 11 Feb 2025

Above information is reliable, but does not constitute warranty.