



Release PP 25 K Dil. 2,0

(Provisional)

Description

RELEASE PP 25 K DIL.2,0 is a polyvinylcarbamate in solvent solution.

Application

The product is a very efficient release agent for polypropilene, polyethylene, PVC, reinforced PVC and polyester films with natural, synthetic rubber and acrylic adhesives. It is also designed to be used with the 3 step printing process of PSA tapes.

Notes

RELEASE PP 25 K DIL.2,0 tends to jellify at temperatures lower than +20°C: the solution becomes hazy and some material settles down to the bottom of the container. It is necessary to restore the original conditions before use, it is sufficient to heat the product at 35-40°C and stir to complete homogeneity.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids Solvents	%	2±0.20 toluene / xylene

Handling

Apply 3 - 5 g/sqm of **RELEASE PP 25 K DIL.2,0** as such or after dilution. Drying must be very efficient, in order to avoid any solvent residue. It can be used on corona treated as well as on untreated films.

Packaging

The product is supplied in Iron drums (20 kg); iron drums (180 kg).

Storing

Product must be stored at temperatures higher than +18°C, far from direct sunlight.

Use within 12 months from production date (unopened and in the original packaging).