



Release G 100 S

(Provisional)

Description

RELEASE G 100 S is a synthetic polymer with high molecular weight in 100% solid powder form. When in solution, it is a very efficient release agent for polyolefins and substrates with low melting points (PE, PP, PVC, PET), coated with natural rubber, synthetic rubber and/or acrylic adhesives. The product is silicone-free.

Application

RELEASE G 100 S can be used on corona treated as well as on untreated films. Recommended concentration ranges from 0.3% to 2% solids, depending upon film, type, coating equipment and desired release force.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	99±0.75
5. Melting Range	°C	76 - 92

Handling

RELEASE G 100 S is soluble in toluene and octane/isopropanol (70/30) at temperatures above 35°C.

In order to achieve a continuous and homogenous coating, the RELEASE G 100 S must be completely dissolved and the solution must be clear and homogeneous.

Slowly add **RELEASE G 100 S** to the solvent and stir continuously at a temperature between 35 and 50°C till complete dissolution of the powder. Handle with care, since the solvent is flammable.

Packaging

The product is supplied in fibre drums (20 kg).

Storing

RELEASE G 100 S in 100% solid form can be stored safely at any temperature below its melting point. In solution, it must be stored at temperatures not below 25°C to prevent gelification. In case of partial or total solidification, store the product in a heated place and stir it well at a temperature between 35°C to 50°C before use. The product will return as fluid as before.

Do not coat if liquid is not completely clear or if gelification occurred.

Use within 24 months from production date (unopened and in the original packaging).