



Handling

Packaging

Storing

containers (800 kg).

prevent loss of solvent.



UNI EN ISO 9001:2015 UNI EN ISO 14001:2015 UNI ISO 45001:2018

SOLACRIL PASS1 is supplied ready for coating by

rotating blade or reverse roll. Diluted, it can be

The product is supplied in ADR compliant IBC

Use within 12 months from production date (unopened and in the original packaging).

Store in a cool place, protected from direct sunlight and heat sources, at temperatures between +5 and +40°C. Keep material in tightly closed containers to

applied by rotogravure or Mayer bar.

# **Solacril Pass 1**

(Provisional)

#### Description

**SOLACRIL PASS1** is a solvent borne acrylic pressure sensitive adhesive with a good tack.

## Application

**SOLACRIL PASS1**, when coated on plastic films (PVC, PET, cellulose acetate), is suitable for the production of industrial pressure sensitive adhesives tapes and decals. It can be applied also on paper, PU foams, fabrics, leather and non wovens.

### **Technical Specifications**

Method of analysis	MU	Standard
1. Total Solids 3. Brookfield Viscosity 25°C	% mPa.s	34±1 7,000 - 12,000 <sup>(I)</sup>
Solvents		heptane / toluene / hexane
<sup>(1)</sup> N. 5 RV; 20 RPM		

### **Film properties**

Method of analysis	MU	Standard	
10. Peel Adhesion on Steel	N/in	10	
22. Static Shear	h	<1	
125. Loop Tack	Ν	<b>12</b> <sup>(1)</sup>	

<sup>(1)</sup> glass

Average values;  $22\pm 2$  g/m<sup>2</sup> of dry adhesive on PET film 36  $\mu$ m

Mod. DT0104E - Solacril Pass 1 Creation date: 8 Mar 2024 Revision: 1 Revision date: 8 Mar 2024

Above information is reliable, but does not constitute warranty.