



# Tackwhite SB5 SL5 V750

## Ammonia Free

(Provisional)

### Description

TACKWHITE SB5 SL5 V750 AMMONIA FREE is a water borne pressure sensitive adhesive, based on an anionic dispersion of a carboxylated SBR latex modified with tackifiers.  
TACKWHITE SB5 SL5 V750 AMMONIA FREE allows to obtain very high peel pressure sensitive adhesives.

### Application

Permanent paper labels, fabrics, synthetic leathers, paper boards, with high adhesive power.

### Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	50±1
3. Brookfield Viscosity 25°C	mPa.s	500 - 1000 <sup>(1)</sup>
8. pH Solvents	pH	6 - 7.5 water

<sup>(1)</sup> N. 2 RV; 20 RPM

### Film properties

Method of analysis	MU	Standard
11. Peel Adhesion on Steel	g/in	2,100
22. Static Shear	h	> 10
97. Loop Tack Test	g	1,600

Average values; 22±2 g/m<sup>2</sup> of dry adhesive on PET film 36 µm

### Handling

The cohesion can be increased by moderate addition (0.2 - 0.4%) of CURING AGENT W3 or CURING AGENT X7. It's important to mix the product well before use.

### Packaging

The product is supplied in iron drums (200 kg); IBC containers (1000 kg).

### Storing

TACKWHITE SB5 SL5 V750 AMMONIA FREE must be stored at temperatures between +5 and +40°C. **STIR WELL BEFORE USE.**

Use within 6 months from production date (unopened and in the original packaging).

### Notes

Formulations based on synthetic latices, once coated, may be subject to a physiological decline of the adhesive performance.