



Storing



UNI EN ISO 9001:2015 UNI EN ISO 14001:2015 UNI ISO 45001:2018

Keep the product at room temperature, protected

Use within 12 months from production date (unopened and in the original packaging).

from humidity and direct sunlight.

# **Antiox 2246**

#### Description

ANTIOX 2246 is a very efficient phenolic antioxidant, suggested for natural rubber or SBR and resins solvent based adhesives.

## **Application**

The stabilization effect in natural rubber/SBR/resin adhesives offers a very good resistance to oxidation and yellowing.

This antioxidant gives protection also towards friction, heat and oxygen effect in the coating process.

ANTIOX 2246 is an antioxidant for natural rubber that has a very good relationship between quality and cost.

#### **Technical Specifications**

Method of analysis	MU	Standard	
5. Melting Range 5. Melting Range	°C °C	128 - 132 128 - 132	
100 Volatiles (I)	%	<1	
100 Volatiles <sup>(1)</sup> 0.	%	<1	
<sup>(1)</sup> 10g/2h/100°C			

### Handling

Suggested usage quantity: 1 part of ANTIOX 22M46 for 100 parts of rubber.

The product can be solved in hexane, acetone and toluene. It has a low volatility.

## Packaging

The product is supplied in fibre drums (40 kg).

Mod. DT0104E - Antiox 2246 Creation date: 17 Mar 1997 Revision: 5 Revision date: 17 Mar 2020

Above information is reliable, but does not constitute warranty.