



Ithane 15

Description

Aromatic thermoplastic polyurethane resin in dry granules.

Application

Suitable for production of flexible and rigid lacquers to be applied by spraying, dipping, coating on: leather, synthetic leathers, shoe soles, etc.

Notes

Solubility:
Methyl Ethyl Ketone (MEK)
Dimethyl Formamide (DMF)
Tetrahydrofuran (THF)
Aceton

Technical Specifications

Method of analysis	MU	Standard
--------------------	----	----------

3. Brookfield Viscosity 25°C	mPa.s	100 - 200 ⁽¹⁾
---------------------------------	-------	--------------------------

⁽¹⁾ 20% TS in MEK

Handling

ITHANE 15 must be dissolved in MEK/Acetone or DMF or blends based on these solvents (10-20%), eventually added with nitro-cellulose, PVC resins and additives.

Packaging

25 kg bags.

Storing

Product must be stored in a dry place at temperatures below 19°C.

Shelf life is 24 months.

Use within 12 months from production date (unopened and in the original packaging).