





## **Tackwhite SBL 15**

**OBSOLETE** 

### **Description**

TACKWHITE SBL 15 is a water-based pressure sensitive adhesive, based on anionic dispersion of latices and resins. It has a long term ageing stability when stored at temperature between +10 and + 40°C.

## **Application**

Permanent paper labels and self adhesive fabrics, synthetic and natural leather, cardboard etc.

### **Technical Specifications**

Method of analysis	MU	Standard
Solvents		water
1. Total Solids	%	
TACKWHITE SBL 15		52±2
3. Brookfield Viscosity 25°C	mPa.s	
TACKWHITE SBL 15		500 - 2,000 <sup>(1)</sup>
8. <b>p</b> H	рН	
TACKWHITE SBL 15		7 - 9
<sup>(1)</sup> N. 2 RV; 20 RPM		

# Film properties

11. Peel Adhesion on Steel	g/in	
TACKWHITE SBL 15		1,600
17. Rolling Ball Tack	cm	
TACKWHITE SBL 15		4
22. Static Shear	h	
TACKWHITE SBL 15		5

Average values;  $22\pm2$  g/m $^2$  of dry adhesive on PET film  $36~\mu m$ 

### **Handling**

TACKWHITE SBL 15 can be transferred to substrates by coating on silicone paper with any method: Meyer bar, reverse roll, rotogravure, knife-over-roll, etc.

The cohesion can be increased by small addition of CURING AGENT W3 or XAMA 7 (ICHEMCO).

## **Packaging**

Product is supplied in 200 I drums or 1000 I tanks.

### **Storing**

TACKWHITE SBL 15 must be stored at temperature between  $+5^{\circ}$ C and  $+40^{\circ}$ C.

If stored in original packaging, shelf life is 3 months.