



Tackwhite AL 4

Description

Carboxylated Styrene-Butadiene water dispersion, soft hand and no residual tack. Good frothing behaviour.

Application

Textile/non woven/paper/leather binder and wet adhesive.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	46±1
8. pH	pH	8
3. Brookfield Viscosity 25°C	mPa.s	50 - 250 ⁽¹⁾
Solvents		water

⁽¹⁾ No 2 RV; 50 RPM

Handling

Can be added with acrylic thickeners to increase viscosity, wetting agents, defoamers, etc. It can be applied by knife, reverse roll, mayer bar, etc.

Packaging

The product is supplied in iron drums (200 kg); IBC containers (1000 kg).

Storing

Keep at temperatures between +5 and 40°C, closed containers.

Use within 6 months from production date (unopened and in the original packaging).