



Storing

between +10 and +40°C.

PROTECT FROM FREEZING



UNI EN ISO 9001:2015 UNI EN ISO 14001:2015 UNI ISO 45001:2018

This product must be stored at a temperature

Use within 6 months from production date (unopened and in the original packaging).

Vinilprimer E5 B1

Description

VINILPRIMER E 5 B1 is a primer for plasticized or rigid PVC films. It is based on a balanced blend of synthetic, natural elastomers and resin dispersions, properly stabilized and compounded.

Application

VINILPRIMER E 5 B1 allows to obtain a perfect adhesion between the adhesive mass (based on natural or synthetic rubbers) and the PVC film, without curing.

It is mainly used for self-adhesive tapes and films, either for packaging or technical use.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids 3. Brookfield Viscosity 25°C	% mPa.s	29±1 50 - 150 (1)
8. pH Solvents	рН	8 - 10 water
⁽¹⁾ No 1 RV; 20 RPM		

Handling

The product can be diluted to a lower viscosity. Thickening: if necessary, with usual acrylic thickeners.

Application: 1.0 - 1.5 g dry/sqm. Stir before usage anche check pH value, it must be between 8 and 10 (if necessary, add ammonia).

Packaging

The product is supplied in iron drums (200 kg); IBC containers (1000 kg).

Mod. DT0104E - Vinilprimer E5 B1 Creation date: 22 Oct 2002 Revision: 7 Revision date: 15 Oct 2018

Above information is reliable, but does not constitute warranty.