





## **Tackwhite A 33**

## **Description**

TACKWHITE A 33 is a pure, water borne acrylic p.s.a. It is a permanent adhesive, suitable for transparent labels, tapes and any pressure sensitive article where a good resistance to the exposure to light is required.

## **Application**

TACKWHITE A 33 is used mainly for permanent label production (paper and film) or foams.

## **Technical Specifications**

Method of analysis	MU	Standard
1. Total Solids 8. pH Solvents	% pH	51±2 8 - 10 water
<ol> <li>Brookfield Viscosity 25°C</li> </ol>	mPa.s	
TACKWHITE A 33 TACKWHITE A 33 (V1)		200 - 500 <sup>(1)</sup> 12000 - 22000 <sup>(2)</sup>

<sup>(</sup>I) No 1 RV; 20 RPM

## Film properties

Method of analysis	MU	Standard
11. Peel Adhesion on Steel	g/in	1,200
22. Static Shear	h	> 50
97. Loop Tack Test	g	800

Average values;  $22\pm2$  g/m<sup>2</sup> of dry adhesive on PET film 36  $\mu$ m

#### **Handling**

The product can be applied by traditional coating method: Mayer bar, reverse roll,... Coating weight depends on the final application, usually it is between 15 and 25 g/sqm dry.

# **Packaging**

The product is supplied in iron drums (200 kg); IBC containers (1000 kg).

## **Storing**

TACKWHITE A 33 must be stored at temperatures between +5°C and +40°C.

Use within 6 months from production date (unopened and in the original packaging).

<sup>(2)</sup> N. 5 RV; 20 RPM