



Storing

upon freezing.

+40°C.

sealed.



UNI EN ISO 9001:2015 UNI EN ISO 14001:2015 UNI ISO 45001:2018

Protect from freezing: containing no freeze/thaw

stabilizers, TACKIFIER 15 coagulates irreversibly

Must be stored at temperature between +5 and

To prevent evaporation and subsequent formation of coarse particles, keep containers or drums well

# **Tackifier 15**

**OBSOLETE** 

#### Description

TACKIFIER 15 is a solvent-free, water borne tackifier dispersion of a mixed alyphatic-aromatic hydrocarbon resin, designed to provide very good adhesive performance to a wide range of substrates.

Ring & Ball value of the base resin =  $85^{\circ}$ C approx.

### Application

TACKIFIER 15 is primarily intended to enhance the pressure sensitive adhesive properties of polymeric latices, such as acrylates or SBR used in the field of self adhesive tapes and labels.

TACKIFIER 15 imparts to the PSA a high adhesion. TACKIFIER 15 is a fine particle size dispersion with excellent mechanical stability for high speed coating, ensuring a wide range of compatibility in both synthetic and natural polymer latices, and improving adhesion to difficult and low surface energy films.

## **Technical Specifications**

1. Total Solids	%	
TACKIFIER 15		51±1.50
3. Brookfield Viscosity 25°C	mPa.s	
TACKIFIER 15		50 - 1,000 <sup>(1)</sup>
8. pH	рН	
TACKIFIER 15		7 - 8
<sup>(1)</sup> N. 2 RV; 20 RPM		

## Packaging

The product is supplied in iron drums (200 kg); IBC containers (1000 kg).

Mod. DT0104E - Tackifier 15 Creation date: 13 Apr 2007 Revision: 6 Revision date: 5 Mar 2015

Above information is reliable, but does not constitute warranty.