



Tackifier 55

Description

TACKIFIER 55 is a water-borne dispersion of modified natural resins. The product is solvent free.
Ring & ball of the base resin = 62-65°C

Application

TACKIFIER 55 is mainly used to modify acrylic, SBR and NR adhesives. It is compatible with a wide range of elastomers. Products containing TACKIFIER 55 are characterized by excellent tack and adhesion.

Notes

The raw materials used in TACKIFIER 55 are listed in FDA 21 CFR 175.105 Adhesives.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	55±1
3. Brookfield Viscosity 25°C	mPa.s	400 - 1000 ⁽¹⁾
8. pH		6.5 - 7.5
⁽¹⁾ N. 2 RV; 20 RPM		

Packaging

The product is supplied in plastic drums (200 kg);
IBC containers (1050 kg).

Storing

Store at temperatures between +5 and +40°C, protected from direct heat sources and direct sunlight.

Use within 6 months from production date
(unopened and in the original packaging).