



Packaging

Storing



UNI EN ISO 9001:2015 UNI EN ISO 14001:2015 UNI ISO 45001:2018

The product is supplied in fibre drums (20 kg).

RELEASE PP 100 is in 100% solid form, and can be

stored safely at almost all normal temperatures

below its melting point. If in solution, it must be

stored at temperatures not below 18°C to prevent

gelification. In case of partial or total solidification,

Do not coat if the solution is not completely clear or

The solution must be handled with caution because of solvent presence (avoid inhalation, skin contact

heat the product and stir well. The product will

Use within 24 months from production date

(unopened and in the original packaging).

become as fluid as before.

if solidification occurs.

and ignition sources).

Release PP 100

Description

RELEASE PP 100 is a synthetic polymer in a 100% solid form. It is usually dissolved in aromatic solvents

(toluene, xylene). It is a very efficient release

agent for adhesive tapes based on following films: PP, PE, PET and PVC, coated

with natural rubber, synthetic rubbers, hot melts and acrylic adhesives.

Application

RELEASE PP 100 can be used on corona treated as well as on untreated PP. Concentrations range goes from 0,5% TS to 3% TS depending on film, coating equipment and desired release performance.

Technical Specifications

| Method of analysis | MU | Standard |
|--------------------|----|----------|
| 1. Total Solids | % | 99±1 |
| 5. Melting Range | °C | 78 - 88 |

Handling

The recommended solvent is toluene, warmed at temperatures higher than 25°C (caution: highly flammable!). Prepare a master solution at 5-10% TS by adding slowly RELEASE PP 100 to the solvent and stir continuously. Dilute this master solution to the final 0.5 - 3% concentration.

Mod. DT0104E - Release PP 100

Creation date: 11 Nov 1996 Revision: 7 Revision date: 22 Mar 2017

1/1

Above information is reliable, but does not constitute warranty.