



# Vinilprimer E 29

(Provisional)

## Description

**VINILPRIMER E 29** is a primer for plasticized or rigid PVC films. It is based on a balanced blend of synthetic, natural elastomers and resin dispersions, properly stabilized and compounded.

## Application

**VINILPRIMER E 29** allows to obtain a perfect adhesion between the adhesive mass (based on natural or synthetic rubbers) and the PVC film, without curing.

It is mainly used for self-adhesive tapes and films, either for packaging or technical use.

## Storing

This product must be stored at a temperature between +10 and +40°C.

PROTECT FROM FREEZING

Use within 6 months from production date (unopened and in the original packaging).

## Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	29±1
3. Brookfield Viscosity 25°C	mPa.s	50 - 150 <sup>(1)</sup>
8. pH Solvents	pH	8 - 10 water

<sup>(1)</sup> No 1 RV; 20 RPM

## Handling

The product can be diluted to a lower viscosity.

Thickening: if necessary, with usual acrylic thickeners.

Application: 1.0 - 1.5 g dry/sqm. Stir before usage anche check pH value, it must be between 8 and 10 (if necessary, add ammonia).

## Packaging

The product is supplied in iron drums (200 kg); IBC containers (1000 kg).