



# Tacksol 20/81934

(Provisional)

## Description

TACKSOL 20/81934 is a solvent pressure sensitive adhesive, based on natural rubber and special resins. After curing, it develops very good resistance to ageing, light and heat.

## Application

TACKSOL 20/81934 can be applied on any substrate (paper, polyester, PP, PE, PVC,...). This product is suggested for the production of protective p.s. films and tapes.

## Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	34±1
3. Brookfield Viscosity 25°C	mPa.s	25000 - 55000
Solvents		hexane / toluene / ethylacetate

## Handling

When heat or mechanical resistance must be increased, 0,5 - 1% of CURING AGENT D should be added, remembering that pot-life of the adhesive in that case is reduced to a maximum of 24 hours.

## Packaging

TACKSOL 20/81934 is supplied in 200 litres (about 140 kg net) iron drums.

## Storing

Use within 12 months from production date (unopened and in the original packaging).

Build date 20 Feb 2026