



# Primer Unisol 11

## Description

PRIMER UNISOL 11 is a solvent borne primer based on special elastomers and resins.

## Application

PRIMER UNISOL 11 is designed to improve anchorage of natural rubber adhesives on PET, PE and PP.

## Storing

The product must be stored at temperatures lower than +40°C. Keep away from direct sunlight. Keep containers tightly closed to prevent solvent evaporation.

Use within 12 months from production date (unopened and in the original packaging).

## Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	8±1
3. Brookfield Viscosity 25°C	mPa.s	80 - 300 <sup>(1)</sup>
Solvents		toluene / ethylacetate

<sup>(1)</sup> No 1 RV; 20 RPM

## Handling

Product must be stirred after long storage; if some solvent is lost for evaporation, add toluene and stir well.

Product must be cured with polyisocyanate, before application: mix 100 w/w of PRIMER UNISOL 11 with 0.7 - 1 w/w of CURING AGENT D and coat with approx. 5-8 g wet/sqm, by reverse roll/gravure/Mayer Bar. Pot life is reduced, as crosslinking starts immediately after the addition of isocyanate.

## Packaging

The product is supplied in iron drums (180 kg).