ichemco
Developing Chemical Excellence

member of Afera

CERTIFIED MANAGEMENT SYSTEMS
CERTIQUALITY
UNI EN ISO **9001:2015**
UNI EN ISO **14001:2015**
UNI ISO **45001:2018**

Primer Unisol 11

Description

PRIMER UNISOL 11 is a solvent borne primer based on special elastomers and resins.

Application

PRIMER UNISOL 11 is designed to improve anchorage of natural rubber adhesives on PET, PE and PP.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	7.5±1
3. Brookfield Viscosity 25°C	mPa.s	80 - 300 (1)
Solvents		toluene / ethylacetate

(1) No 1 RV; 20 RPM

Handling

Product must be stirred after long storage; if some solvent is lost for evaporation, add toluene and stir well.

Product must be cured with polyisocianate, before application: mix 100 w/w of PRIMER UNISOL 11 with 0.7 - 1 w/w of CURING AGENT D and coat with approx. 5-8 g wet/sqm, by reverse roll/gravure/Mayer Bar. Pot life is reduced, as crosslinking starts immediately after the addition of isocyanate.

Packaging

The product is supplied in iron drums (180 kg).

Storing

The product must be stored at temperatures lower than +40°C. Keep away from direct sunlight. Keep containers tightly closed to prevent solvent evaporation.

Use within 12 months from production date (unopened and in the original packaging).

Build date 11 Sep 2025

Above information is reliable, but does not constitute warranty.

ICHEMCO srl
via 11 Settembre, 5 - 20012 CUGGIONO (MI) - ITALY
Phone: +39 02 97243.1 - info@ichemco.it - www.ichemco.it