



Packaging

drums (20 kg).

Storing



UNI EN ISO 9001:2015 UNI EN ISO 14001:2015 UNI ISO 45001:2018

The product is supplied in tins (0.500 kg); Iron

moisture. Reaction with water or moisture can form solid insoluble polyureas, which can block pipes.

valves, etc. CURING AGENT W3 DIL must be stored

aluminum/glass bottles, at temperatures between

10°C and 30°C. At higher temperatures it can

Polyisocyanates are very sensitive to

in well sealed original plastic drums or

develop hazardous vapors.

Curing Agent W3 DIL

OBSOLETE

Description

CURING AGENT W3 DIL is a water dispersable polyisocyanate, NCO content is about 13%. Adhesive emulsions or solutions can be efficiently cross-linked with this product. The cured adhesive will have an increased resistance to heat, water, plasticizers and organic solvents.

Application

CURING AGENT W3 DIL is suggested for water borne adhesives, paints, lacquers. It is used at 0.3 - 3.5%, depending on the material to be cross-linked and desired results. Check the behaviour of the crosslinked product after 24-48 hours from application.

Technical Specifications

| MU | Standard | |
|----|----------|--------------|
| | acetone | |
| % | | |
| | 70±1 | |
| | | acetone % |

Handling

CURING AGENT W3 DIL must be added just before application and stirred till complete homogeneity. Reaction starts immediately, so we recommend to use the product just after activation. The crosslinking mechanism depends on different aspects such as adhesive concentration, amount of crosslinker, temperature. We suggest to check the curing conditions in advance, in order to avoid to spoil material.

Mod. DT0104E - Curing Agent W3 DIL Creation date: 24 Oct 2001 Revision: 5 Revision date: 6 Mar 2019

Above information is reliable, but does not constitute warranty.