Tacksol SM 3

Description

TACKSOL SM 3 is a solventborne pressure sensitive adhesive, based on natural rubber and special synthetic resins as tackifiers.

Application

TACKSOL SM 3 has been designed to be used for the production of single or double-sided adhesive foams.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids	%	32±2
3. Brookfield Viscosity 25°C	mPa.s	15000 - 30000 (1)
Solvents		hexane

(1) No 5 RV; 10 RPM

Film properties

Method of analysis	MU	Standard
10. Peel Adhesion on Steel	N/in	13
22. Static Shear	h	> 100
125. Loop Tack	N	15

Average values; 22±2 g/m² of dry adhesive on PET film 36 µm

Handling

The product must be coated as it is, by standard coating systems.

Packaging

The product is supplied in iron drums (145 kg).

Storing

Product must be stored at temperatures between +5°C and +30°C, in closed containers. Keep away from direct sunlight and ignition sources.

Use within 12 months from production date (unopened and in the original packaging).

Build date 11 Sep 2025

Above information is reliable, but does not constitute warranty.

ICHEMCO srl
via 11 Settembre, 5 - 20012 CUGGIONO (MI) - ITALY
Phone: +39 02 97243.1 - info@ichemco.it - www.ichemco.it