Primer PP 10

Description

Primer PP 10 is a solvent borne primer for polyolefinic films and natural rubber based adhesives.

Application

Primer PP 10 has been developed for the application of treated polyolefin films.

Technical Specifications

Method of analysis	MU	Standard
1. Total Solids Solvents	%	10±0.50 toluene

Handling

The application systems can be reverse-roll and Mayer bar.

Primer PP 10 must be activated prior to its use by adding 1-1.5% of Curing Agent D, the pot-life of the product is reduced as crosslinking starts immediately after the addition of the curing agent.

Stir well after activation. Apply 0.5-0.6 g dry/sqm. If necessary, the product can be diluted with toluene.

Packaging

The product is supplied in iron drums (180 kg).

Storing

Store the product at room temperature, protected from direct sunlight and humidity. Stir weel before use.

Use within 12 months from production date (unopened and in the original packaging).

Build date 11 Sep 2025

Above information is reliable, but does not constitute warranty.

ICHEMCO srl
via 11 Settembre, 5 - 20012 CUGGIONO (MI) - ITALY
Phone: +39 02 97243.1 - info@ichemco.it - www.ichemco.it